Arrowhead®

Technical Data Sheet

Arrowhead® Flex Panel System

SYSTEM OVERVIEW

Compatible Materials	4mm FR Core Metal Composite Material ≤3mm (1/8") Solid Aluminum Plate >2mm (0.080") Aluminum Plate
Extrusions & Clips	Aluminum Alloy 6063-T6
Fabrication Method	Shop fabricated CNC Router recommended
Panel Assembly	Rout-and-Return Riveted System
Installation Methods	Clip Installation Grid Installation RapidWrapCI® (uses Grid Installation)

ARROWHEAD LEED DATA

½ Pre-Consumer + Post-Consumer Recycled Content	
Arrowhead® Extrusions	Up to 44.5%

PANEL SIZES

Max. Recommended Panel Size	60" x 96" (larger sizes may require additional handling)
Typical Stiffener Spacing	24" o.c. (engineered per project)

FLORIDA PRODUCT APPROVAL

Product Approval Number	46016.1

DrJ TECHNICAL EVALUATION REPORT

TER 2006-02

Access the most recent **Arrowhead®** Technical Evaluation Report by DrJ Engineering by scanning the QR code or clicking the link below:

https://www.drjcertification.org/ter/2006-02

CHEMICAL COMPOSITION (6063-T6)

Standard	Element	Content
ASTM B221	Aluminum (Al)	97.5% - 99.3%
ASTM B221	Magnesium (Mg)	0.45% - 0.90%
ASTM B221	Silicon (Si)	0.20% - 0.60%
ASTM B221	Iron (Fe)	0.00% - 0.35%
ASTM B221	Copper (Cu)	0.00% - 0.10%
ASTM B221	Manganese (Mn)	0.00% - 0.10%
ASTM B221	Chromium (Cr)	0.00% - 0.10%
ASTM B221	Zinc (Zn)	0.00% - 0.10%
ASTM B221	Titanium (Ti)	0.00% - 0.10%
ASTM B221	Other	0.05% - 0.15%

AAMA 508 PRESSURE EQUALIZED ARROWHEAD RAIN SCREEN

Standard	Test	Test Standard	Result
ASTM E283	Air Leakage of Test Buck (without panel system installed)	0.11 cfm/ft² min. 0.13 cfm/ft² max.	PASS
ASTM E1233	Cyclic Static Air Pressure Differential (pressure cycling)	Cycle Time Lag 0.08 sec max. Cycle Pressure Difference 12.5 psf max.	PASS
ASTM E331	Static Water Penetration	3.20 ft²	PASS
AAMA 501.1	Dynamic Water Penetration	3.20 ft²	PASS
ASTM E330	Uniform Load Deflection and Uniform Load Structural	L/175 of Stiffener Length	PASS

AAMA 509 DRAINED AND BACK VENTILATED ARROWHEAD RAIN SCREEN

Standard	Test	Arrowhead FLEX Results
ASTM E283	Air Leakage	V3
ASTM E331	Static Water Penetration	W1
AAMA 501.1	Dynamic Water Penetration	W1

FLORIDA PRODUCT APPROVAL - HIGH-VELOCITY HURRICANE ZONE

Standard	Test	Test Standard	Result
TAS 202-94	Uniform Static Air Pressure	(+100/-150 psf)	PASS
TAS 201-94	Large Missile Impact Procedures	(+100/-150 psf)	PASS
TAS 203-94	Cyclic Winds Pressure Loading	(+100/-150 psf)	PASS

THERMAL PERFORMANCE

Standard	Descriptions	Test
ASTM D696	Coefficient of Linear Expansion	13.8 x 10^{-6} in/in/°F (Aluminum)

FIRE PERFORMANCE

Standard	Descriptions	Test	Test Result
ASTM E136	Fire Performance of Aluminum	ΔT < 86°F	Non-Combustible
NFPA 285	Fire Propagation Characteristics	PASS/FAIL	PASS

MECHANICAL PROPERTIES (6063-T6)

Standard	Property	Data
ASTM B221	Elastic (Young's, Tensile) Modulus	9.9 x 10^6 psi
ASTM B221	Elongation at Break	11%
ASTM B221	Fatigue Strength	10 x 10^3 psi
ASTM B221	Poisson's Ratio	0.33
ASTM B221	Shear Modulus	3.7 x 10^6 psi
ASTM B221	Shear Strength	22 x 10^3 psi
ASTM B221	Tensile Strength: Ultimate (UTS)	35 x 10^3 psi
ASTM B221	Tensile Strength: Yield (Proof)	30 x 10^3 psi

Data are typical, are provided for informational purposes, and should not be construed as maximum or minimum values for specification or for final design, or for a particular use or application. The data may be revised anytime without notice. We make no representation or warranty as to its accuracy and assume no duty to update. Actual data on any particular product or material may vary from those shown herein. © 2026 Fairview Architectural. All rights reserved.